



EAGLE 865

High strength low heat electrode for joining and buildup of dissimilar steels.

APPLICATIONS

For build-up and joining of all grades of low alloy steels, tool steels, high alloy steels and carbon steels. This electrode can be used for rebuilding shafts, forging dies, hot shearing blades, dies, punches, conveyor chains and debarker knives.

PROCEDURE

AC or DC reverse polarity (+). Clean weld areas with a grinder. Preheat carbon steels to 400°F. Maintain a short arc and stringer beads are recommended to prevent overheating. Allow to cool before removing slag.

GENERAL CHARACTERISTICS

The **EAGLE 865** has a low heat input with excellent welding properties. It is heat resistant, corrosion resistant and is designed to produce the high tensile strength welds needed in today's welding industry.

TECHNICAL DATA

Tip: Color:	Blue						
Tensile Strength: Psi	Approx 120,000						
Elongation:	30 - 35%						
Current:	AC - DC Reverse (+)						
Sizes (IN)		1/16	5/64	3/32	1/8	5/32	3/16
(MM)		1.60	2.00	2.50	3.25	4.00	5.00
Amperage:		20 - 40	40 - 60	60 - 80	90 - 120	125 - 160	160 - 180

www.eaglealloys.ca