



EAGLE 328 LT

SPRAY ALLOY POWDER

Economical High Quality Aluminum Bronze

APPLICATIONS

The **EAGLE 328 LT** is an excellent build-up on pump impeller shafts, pistons, conveyor shafts, bell housings and cylindrical surfaces.

PROCEDURE

Set acetylene at 5 psi and Oxygen at 11 - 13 psi. Set torch to an oxidizing flame. Place the torch in a horizontal position to the work piece at a distance of 6" - 7" and traverse back and forth, fully covering the bond coat area to the required thickness plus .020". Do not overheat and do not exceed 700° F. Use 600° tempil sticks to check temperature. Allow to cool in the lathe before finishing. Use a sharp Carbide tool bit starting in the center of the deposit and working alternately towards each end.

GENERAL CHARACTERISTICS

The **EAGLE 328 LT** is a high quality, economical aluminum bronze powder that is fully machinable. This powder is a self-lubricating low friction finish for bearing surfaces on all metals except pure copper.

TECHNICAL DATA

Hardness: (RB) Approx. 65
Machinability: Excellent
Gas Pressure: Acetylene: 5 psi
 Oxygen: 11 - 13 psi



≡ HIGH QUALITY WELDING PRODUCTS ≡

10077 - 166 STREET, EDMONTON, ALBERTA T5P 4Y1 • BUS: (780) 481-8082
FOR TECHNICAL ASSISTANCE CALL US TOLL FREE 1-800-447-1415

REVISED 01 2024